



WINGUM PLUS H₂O

Art. code see DDT

Date of issue 04.05.2018

Review nr. 12

Page 1 of 5

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

DESCRIPTION OF THE PRODUCT

Coloured waterproofing water-based liquid membrane based on modified resins. Ideal also for large surfaces. WINGUM PLUS H₂O gained ICC-ES DoP, according to ASTM D 6083 regulation, MIAMI DADE COUNTY acknowledgment, and CRRC certification. It is also certified in AEU. It meets the ETAG 005 guide lines, about liquid products applied as waterproofing ones.

USE FIELDS

Its particular formulation, allows high flexibility, the product is stable also at very low temperatures. It normally step steady. WINGUM PLUS H₂O is suitable where very good resistance to backwater is required, also on flat surfaces subject to stagnation. It has an excellent resistance to ageing and U.V. rays. Suitable for waterproofing of concrete supports, fibre-cement slabs, metal sheds also oxidisable, woods, ceramic tiles or natural stone floorings, brickworks, bitumen-polymer membranes (oxidizes for a minimum of 180 days), XPS, EPS and polyurethane insulating panels.

SURFACE PREPARATION

Accurately clean the support to eliminate: dust, crumbly parts, foreign or bonding-proof matters. Surface must be perfectly dry. On irregular supports, it is advisable making a previous application of WINFIX CONCRETE, in order to allow adhesion. Check foundation wet to avoid onset of air bubbles due to vapour pressure. The best procedure is the application of a polyethylene sheet sealed by means of bonding tape on the side of the surface exposed to the sun and to check after 24 hours possible condensation water. If there is no condensation water, lay WINGUM PLUS H₂O, on the contrary, wait for full drying.

ADVICES

- Do not add any additive.
- Do not use the packaging if damaged.
- Do not add water nor solvents.

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



WINGUM PLUS H₂O

Art. code see DDT

Date of issue 04.05.2018

Review nr. 12

Page 2 of 5

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

WARNING

In case WINGUM PLUS H₂O should be applied on a bituminous membranes it must have undergone at least 180 days of oxidization before starting to apply the product. Apply WINGUM PLUS H₂O at temperatures between +5°C and +35°C. protect it from water, rain and snow during the first 24 hours from its application. Do not apply if night dampness is imminent.

APPLICATION

The product is ready to use and can be applied with short-bristle roller for solvent, brush, large paintbrush, steel plastering towel and airless gun.

Apply at least two coats of the product to achieve homogenous thickness, ideal for waterproofing. In order to assure waterproofing function, on perimeter edges of the surface, apply the waterproofing adhesive band BC SEAL BAND. For waterproofing and sealing around roof penetrations such as drain, ventilation pipes, other roof penetrations or around plumbing pipes and drains, use BC SEAL PAD, self-adhesive butyl square pad.

APPLICATION WITH REINFORCEMENT

On supports particularly subject to deformation, also considerable, therefore presenting a high risk for cracking, please reinforce WINGUM PLUS H₂O with WINTECHNO MAT.

Application must be carried out as follows:

Apply WINGUM PLUS H₂O in a uniform coat on the support, lay over the WINTECHNO MAT using the steel plastering trowel to ensure the adherence of the mat to the liquid membrane. Let the product to fully dry (18-24 hours) and then resume the application of the second coat of WINGUM PLUS H₂O until getting the consumption indicated in the technical data sheet.

SURFACES WITH JOINTS

Use WINJOINT BAND, waterproof elastic band made of rubber and polyester fabric, suitable for waterproofing structural joints.

Apply WINJOINT BAND as described below: clean the surface to be treated, apply WINGUM PLUS H₂O laterally to the joint and to a width that is larger than the joint cover. Apply the joint cover by placing the lateral perforated strip to the area already treated

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



WINGUM PLUS H₂O

Art. code see DDT

Date of issue 04.05.2018

Review nr. 12

Page 3 of 5

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

with WINGUM PLUS H₂O. Once dry, soak it with a further coat of product.

CONSUMPTION

1.2 – 1.4 kg/m² in two coats.

1.8 – 2.0 kg/m² on concrete in two coats with reinforcement interposed.

PACKAGING

5-10-20 kg buckets.

STORAGE

The product in its undamaged packaging can be stored for 24 months. The products can be stored also at temperature between +5°C and +40°C. It is not frost-proof.

SAFETY INSTRUCTIONS

PRECAUTIONS

For information about safety, user must refer to the most recent Safety Data Sheet, edited in accordance with the regulations in force, which contains physical, toxic and other data about the product in use.

ECOLOGY

Do not through out the product and/or empty containers in the environment. Consult the most recent Safety Data Sheet for further information about disposals.

TECHNICAL FEATURES

PRODUCT FEATURES

Look	Fibred fluid paste
Colour	White, grey, red, green
Specific weight at 20°C (g/cm ³)	1.45 ± 0.05

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT



WINGUM PLUS H₂O

Art. code see DDT

Date of issue 04.05.2018

Review nr. 12

Page 4 of 5

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

Solid content (%)	75 ± 3
Brookfield viscosity at 20°C (cps)	18,000 ± 2000

OPERATIONAL PRODUCT PERFORMANCES

Resistant to temperatures	-30°C +80°C
Resistance to atmospheric agents	Good
Resistance to U.V. rays	Excelent

Tensile and elongation strenght at break before accelerated ageing (ASTM D 2370)

Resistance at break (N/mm ²)	Elongation (%)
1.41	438

Tensile and elongation strength at break after 1000h of accelerated ageing (ASTM D 2370)

Resistance at break (N/mm ²)	Elongation (%)
1.66	247

Perms ASTM D 1653 Method B Condition A

Value	Required
10	≤ 50

Mold resistance (evaluation) ASTM G 21

Value	Required
0	0

Strength at break (lbf/in) ASTM D 624

Value	Required
106	≥60

Water absorption (ASTM D 471) before accelerated ageing

Days into water	Absorption (% on weight)
7 ± 4h	17

To the best of our knowledge, the information contained in this prospectus are correct and accurate, but every recommendation and suggestion is given without any guarantees, as the using conditions are not under our direct control. It is advisable to always perform some preliminary tests.
Our company reserves the right to modify the products and the content of this document without any warning.
The present edition annuls and replaces any other previous edition.

IN CASE OF DOUBT PLEASE CONSULT OUR TECHNICAL SUPPORT

Via M. Buonarroti, 15 – 20093 Cologno M.se (MI) – Italia Tel. +39 02/267.00.605 – Fax +39 02/267.00.621 –
info@winklerchimica.com www.winklerchimica.com

Water absorption (ASTM D 471) after 1000 h of accelerated ageing

Days into water	Absorption (% on weight)
7 ± 4h	6

Flexibility at low temperatures (ASTM D 522) before accelerated ageing

Temperature (°C)	Break (Y/N)
-26	N

Flexibility at low temperatures (ASTM D 522) after 1000 h of accelerated ageing

Temperature (°C)	Break (Y/N)
-26	N

Resistance to accelerated ageing cycles (ASTM D 4798)

QUV Machine: Accelerated Weathering Tester. Model QUV/Spray

Hours	Cracks shown
1,000	N

Resistance to abrasion ETAG 008

Number of passages	Weight loss (%)
10,000	0

Adhesion before sun-rain cycles, 25 cycles

Dynamometer meeting UNI EN 1348-2000

Support	Before cycles	After cycles	Required
Concrete	1.45 N/mm ²	1.20 N/mm ²	≥ 1.0 N/mm ²
Ceramic	1.70 N/mm ²	1.55 N/mm ²	≥ 1.0 N/mm ²

The product meets with prescriptions of Directive 2003/53/CE.